

Akulon[®] S223-D

Property Data

PA66

Low/Medium Viscosity, Nucleated

Properties	Typical Data	Unit	Test Method
RHEOLOGICAL PROPERTIES			
	dry / cond		
Molding shrinkage (parallel)	0.95 / *	%	ISO 294-4
Molding shrinkage (normal)	0.95 / *	%	ISO 294-4
MECHANICAL PROPERTIES			
	dry / cond		
Tensile modulus	3600 / 1600	MPa	ISO 527-1/-2
Yield stress	95 / 60	MPa	ISO 527-1/-2
Yield strain	4 / 20	%	ISO 527-1/-2
Nominal strain at break	10 / >50	%	ISO 527-1/-2
Flexural modulus	2800 / -	MPa	ISO 178
Flexural strength	125 / -	MPa	ISO 178
Charpy impact strength (+23°C)	N / N	kJ/m ²	ISO 179/1eU
Charpy impact strength (-30°C)	N / N	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	6 / 12	kJ/m ²	ISO 179/1eA
Charpy notched impact strength (-30°C)	6 / 6	kJ/m ²	ISO 179/1eA
THERMAL PROPERTIES			
	dry / cond		
Melting temperature (10°C/min)	260 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	85 / *	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	230 / *	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	1 / *	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	1 / *	E-4/°C	ISO 11359-1/-2
Burning Behav. at 1.5 mm nom. thickn.	V-2 / *	class	IEC 60695-11-10
Thickness tested	1.5 / *	mm	IEC 60695-11-10
Burning Behav. at thickness h	V-2 / *	class	IEC 60695-11-10
Thickness tested	0.75 / *	mm	IEC 60695-11-10
ELECTRICAL PROPERTIES			
	dry / cond		
Relative permittivity (100Hz)	3.2 / 15	-	IEC 60250
Relative permittivity (1 MHz)	3 / 4.3	-	IEC 60250
Dissipation factor (100 Hz)	60 / 2400	E-4	IEC 60250
Dissipation factor (1 MHz)	170 / 1200	E-4	IEC 60250
Volume resistivity	1E13 / 1E10	Ohm*m	IEC 60093
Surface resistivity	* / 1E14	Ohm	IEC 60093
Electric strength	30 / 25	kV/mm	IEC 60243-1
Comparative tracking index	* / 600	-	IEC 60112
OTHER PROPERTIES			
	dry / cond		
Water absorption	8.5 / *	%	Sim. to ISO 62
Humidity absorption	2.3 / *	%	Sim. to ISO 62

20.05.2009

All information supplied by or on behalf of DSM in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and, in good faith, believed reliable, but DSM assumes no liability and makes no warranties of any kind, express or implied, including, but not limited to, those of title, merchantability, fitness for a particular purpose or non-infringement or any warranty arising from a course of dealing, usage, or trade practice whatsoever in respect of application, processing or use made of the aforementioned information or product. The user assumes all responsibility for the use of all information provided and shall verify quality and other properties or any consequence from the use of all such information. Typical values are indicative only and are not to be construed as being binding specifications.

Akulon[®] S223-D

Density	1140 / -	kg/m ³	ISO 1183
---------	----------	-------------------	----------

20.05.2009

All information supplied by or on behalf of DSM in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and, in good faith, believed reliable, but DSM assumes no liability and makes no warranties of any kind, express or implied, including, but not limited to, those of title, merchantability, fitness for a particular purpose or non-infringement or any warranty arising from a course of dealing, usage, or trade practice whatsoever in respect of application, processing or use made of the aforementioned information or product. The user assumes all responsibility for the use of all information provided and shall verify quality and other properties or any consequence from the use of all such information. Typical values are indicative only and are not to be construed as being binding specifications.