

(PC+PET)

Properties	Typical Data	Unit	Test Method
RHEOLOGICAL PROPERTIES			
Melt volume-flow rate	7	cm ³ /10min	ISO 1133
Temperature	280	°C	ISO 1133
Load	1.2	kg	ISO 1133
MECHANICAL PROPERTIES			
Tensile modulus	2200	MPa	ISO 527-1/-2
Yield stress	55	MPa	ISO 527-1/-2
Yield strain	6	%	ISO 527-1/-2
Nominal strain at break	>50	%	ISO 527-1/-2
Flexural modulus	2200	MPa	ISO 178
Flexural strength	80	MPa	ISO 178
Charpy impact strength (+23°C)	N	kJ/m ²	ISO 179/1eU
Charpy impact strength (-30°C)	N	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	55	kJ/m ²	ISO 179/1eA
Charpy notched impact strength (-30°C)	25	kJ/m ²	ISO 179/1eA
Izod notched impact strength (23°C)	70	kJ/m ²	ISO 180/4A
Izod notched impact strength (-20°C)	60	kJ/m ²	ISO 180/4A
Izod notched impact strength (-40°C)	40	kJ/m ²	ISO 180/4A
THERMAL PROPERTIES			
Temp. of deflection under load (1.80 MPa)	120	°C	ISO 75-1/-2
Vicat softening temperature (50°C/h 50N)	130	°C	ISO 306
Coeff. of linear therm. expansion (parallel)	0.8	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	0.8	E-4/°C	ISO 11359-1/-2
Burning Behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.5	mm	IEC 60695-11-10
OTHER PROPERTIES			
Water absorption	0.35	%	Sim. to ISO 62
Density	1210	kg/m ³	ISO 1183
RHEOLOGICAL CALCULATION PROPERTIES			
Thermal conductivity of melt	0.162	W/(m K)	-
Spec. heat capacity melt	2110	J/(kg K)	-

10.03.2009

All information supplied by or on behalf of DSM in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and, in good faith, believed reliable, but DSM assumes no liability and makes no warranties of any kind, express or implied, including, but not limited to, those of title, merchantability, fitness for a particular purpose or non-infringement or any warranty arising from a course of dealing, usage, or trade practice whatsoever in respect of application, processing or use made of the aforementioned information or product. The user assumes all responsibility for the use of all information provided and shall verify quality and other properties or any consequence from the use of all such information. Typical values are indicative only and are not to be construed as being binding specifications.