

SABIC® PP FPC55

PP block copolymer FLOWPACT for Injection moulding

Description: SABIC® PP FPC55 is a grade developed for the thin wall packaging market. The grade is nucleated and is characterised by excellent flow behaviour in combination with an improved stiffness to impact balance. SABIC® PP FPC55 allows for very cost efficient processing on the basis of easy mould filling, short cycle times and improved part consistency in combination with pigments. It contains an antistatic package.

Application: SABIC® PP FPC55 is typically used in thin wall packing applications both for food and non-food segments. This includes pails & containers, yellow fats/margarine tubs and dairy cups. In de caps and closure segment, the grade could be used for thin walled spray through caps, amongst other. The grade has excellent heat deflection temperature making it particularly suitable for hot fill applications.

Health, Safety and Food Contact regulation: Material Safety Data Sheets (MSDS) and Product Safety declarations are available on our Internet site <http://www.SABIC-europe.com>.

-The product mentioned herein is in particular not tested and therefore not validated for use in pharmaceutical/ medical applications.

This grade material is UL registered under File E111275 (www.ul.com) / IMDS 80775790

Typical values

Revision 20150303


Properties	Unit (Si)	Values	Test methods
Polymer properties			
Melt flow rate (MFR) at 230 °C and 2.16 kg	dg/min	55	ISO 1133
Density	kg/m ³	905	ISO 1183
Formulation			
Anti static agent	-	Yes	-
Nucleating agent	-	Yes	-
Mechanical properties			
Tensile test			ISO 527-2 1A
stress at yield ¹⁾	MPa	25	
strain at yield ¹⁾	%	4	
tensile modulus ²⁾	MPa	1500	
Izod impact notched			ISO 180/1A
at 23 °C	kJ/m ²	8	
at 0 °C	kJ/m ²	6	
at -20 °C	kJ/m ²	5	
Charpy impact notched			ISO 179/1eA
at 23 °C	kJ/m ²	9	
at 0 °C	kJ/m ²	7	
at -20 °C	kJ/m ²	5	
Hardness Shore D	-	62	ISO 868
Thermal properties			
Heat deflection temperature ³⁾			ISO 75
at 1.80 MPa (HDT/A)	°C	55	
at 0.45 MPa (HDT/B)	°C	95	
Vicat softening temperature ⁴⁾			ISO 306
at 10 N (VST/A)	°C	150	
at 50 N (VST/B)	°C	76	

1) Speed of testing: 50 mm/min

2) Speed of testing: 1 mm/min

3) Flat wise (testbar 80*10*4mm)

4) Temperature rate: 120°C/h



SABIC® PP FPC55

PP block copolymer FLOWPACT for Injection moulding

Quality:

SABIC Europe is fully certified in accordance with the internationally accepted quality standard ISO9001.

Storage and handling:

Avoid prolonged storage in open sunlight, high temperatures (<50 °C) and /or high humidity as this could well speed up alteration and consequently loss of quality of the material and /or its packaging. Keep material completely dry for good processing.

Disclaimer. The information contained herein may include typical properties of our products or their typical performances when used in certain typical applications. Actual properties of our products, in particular when used in conjunction with any third party material(s) or for any non-typical applications, may differ from typical properties.

It is the customer's responsibility to inspect and test our product(s) in order to satisfy itself as to the suitability of the product(s) for its and its customers particular purposes. The customer is responsible for the appropriate, safe and legal use, processing and handling of all product(s) purchased from us.

Nothing herein is intended to be nor shall it constitute a warranty whatsoever, in particular, warranty of merchantability or fitness for a particular purpose.

SABIC as referred to herein means any legal entity belonging to the group of companies headed by SABIC Europe B.V.