



## SABIC® PP 513MNK40

### PP block copolymer for Injection moulding

#### Description:

This very high flow grade shows a medium impact resistance, even at low temperatures, combined with high stiffness. SABIC® PP 513MNK40 is provided with an anti-static package. It is used for high speed processing of thin walled packaging articles like margarine tubs, ice cream containers and flowerpots. SABIC® PP 513MNK40 can also be applied for use in caps and closures, toys and housewares. This grade is also available without anti-static additives.

#### Health, Safety and Food Contact regulations:

Material Safety Data Sheets (MSDS) and Product Safety declarations are available on our Internet site <http://www.SABIC-europe.com>

The product mentioned herein is in particular not tested and therefore not validated for use in pharmaceutical/ medical applications.

This grade material is UL registered under File E111275 ([www.ul.com](http://www.ul.com))


IMDS 80775790

#### Typical values

Revision 20140109

Properties	Unit (Si)	Values	Test methods
<b>Polymer properties</b>			
<b>Melt flow rate (MFR)</b> at 230 °C and 2.16 kg	dg/min	<b>70</b>	ISO 1133
<b>Density</b>	kg/m <sup>3</sup>	<b>905</b>	ISO 1183
<b>Formulation</b>			
<b>Anti static agent</b>	-	<b>Yes</b>	-
<b>Nucleating agent</b>	-	<b>Yes</b>	-
<b>Mechanical properties</b>			
<b>Tensile test</b>			ISO 527-2 1A
stress at yield <sup>1)</sup>	MPa	<b>25</b>	
strain at yield <sup>1)</sup>	%	<b>4</b>	
tensile modulus <sup>2)</sup>	MPa	<b>1350</b>	
<b>Izod impact notched</b>			ISO 180/1A
at 23 °C	kJ/m <sup>2</sup>	<b>7</b>	
at 0 °C	kJ/m <sup>2</sup>	<b>5</b>	
<b>Charpy impact notched</b>			ISO 179/1eA
at 23 °C	kJ/m <sup>2</sup>	<b>8</b>	
at 0 °C	kJ/m <sup>2</sup>	<b>7</b>	
<b>Hardness Shore D</b>	-	<b>62</b>	ISO 868
<b>Thermal properties</b>			
<b>Heat deflection temperature</b> <sup>3)</sup>			ISO 75
at 1.80 MPa (HDT/A)	°C	<b>55</b>	
at 0.45 MPa (HDT/B)	°C	<b>90</b>	
<b>Vicat softening temperature</b> <sup>4)</sup>			ISO 306
at 10 N (VST/A)	°C	<b>150</b>	
at 50 N (VST/B)	°C	<b>75</b>	

- 1) Speed of testing: 50 mm/min
- 2) Speed of testing: 1 mm/min
- 3) Flat wise ( testbar 80\*10\*4mm)
- 4) Temperature rate: 120°C/h



## SABIC® PP 513MNK40

### PP block copolymer for Injection moulding

**Quality:**

SABIC Europe is fully certified in accordance with the internationally accepted quality standard ISO9001.

**Storage and handling:**

Avoid prolonged storage in open sunlight, high temperatures (<50 °C) and /or high humidity as this could well speed up alteration and consequently loss of quality of the material and /or its packaging. Keep material completely dry for good processing.

**Disclaimer.** The information contained herein may include typical properties of our products or their typical performances when used in certain typical applications. Actual properties of our products, in particular when used in conjunction with any third party material(s) or for any non-typical applications, may differ from typical properties.

It is the customer's responsibility to inspect and test our product(s) in order to satisfy itself as to the suitability of the product(s) for its and its customers particular purposes. The customer is responsible for the appropriate, safe and legal use, processing and handling of all product(s) purchased from us.

Nothing herein is intended to be nor shall it constitute a warranty whatsoever, in particular, warranty of merchantability or fitness for a particular purpose.

SABIC Europe as referred to herein means any legal entity belonging to the SABIC Europe group of companies.