

Arnite[®] TV4 260 S

PBT-GF30 FR(17)

30% Glass Reinforced, Flame Retardant

Print Date: 2016-04-01

Properties	Typical Data	Unit	Test Method
Rheological properties			
Molding shrinkage [normal]	1.4	%	Sim. to ISO 294-4
Molding shrinkage [parallel]	0.6	%	Sim. to ISO 294-4
Thickness tested	3	mm	ISO 294-4
Mechanical properties			
Tensile modulus	11500	MPa	ISO 527-1/-2
Stress at break	135	MPa	ISO 527-1/-2
Strain at break	2	%	ISO 527-1/-2
Charpy impact strength (+23 °C)	50	kJ/m ²	ISO 179/1eU
Charpy impact strength (-30 °C)	55	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23 °C)	8	kJ/m ²	ISO 179/1eA
Charpy notched impact strength (-30 °C)	10	kJ/m ²	ISO 179/1eA
Thermal properties			
Melting temperature (10 °C/min)	225	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	210	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	220	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	0.35	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	0.7	E-4/°C	ISO 11359-1/-2
Burning Beh. at 1.5 mm nom. thickn.	V-0	class	IEC 60695-11-10
Thickness tested	1.5	mm	IEC 60695-11-10
Burning Beh. at thickness h	V-2	class	IEC 60695-11-10

All information supplied by or on behalf of DSM in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and, in good faith, believed reliable, but DSM assumes no liability and makes no warranties of any kind, express or implied, including, but not limited to, those of title, merchantability, fitness for a particular purpose or non-infringement or any warranty arising from a course of dealing, usage, or trade practice whatsoever in respect of application, processing or use made of the aforementioned information or product. The user assumes all responsibility for the use of all information provided and shall verify quality and other properties or any consequence from the use of all such information. Typical values are indicative only and are not to be construed as being binding specifications.

Properties	Typical Data	Unit	Test Method
Thickness tested	0.5	mm	IEC 60695-11-10
Oxygen index	36	%	ISO 4589-1/-2
Glow Wire Flammability Index GWFI	960	°C	IEC 60695-2-12
GWFI (Thickness (1) tested)	0.75	mm	IEC 60695-2-12
Glow Wire Flammability Index GWFI	960	°C	IEC 60695-2-12
GWFI (Thickness (2) tested)	1.5	mm	IEC 60695-2-12

Electrical properties


Relative permittivity (100Hz)	4.1	-	IEC 60250
Relative permittivity (1 MHz)	3.9	-	IEC 60250
Dissipation factor (100 Hz)	20	E-4	IEC 60250
Dissipation factor (1 MHz)	150	E-4	IEC 60250
Volume resistivity	>1E13	Ohm*m	IEC 60093
Electric strength	28	kV/mm	IEC 60243-1
Comparative tracking index	250	-	IEC 60112

Other properties

Water absorption	0.3	%	Sim. to ISO 62
Humidity absorption	0.15	%	Sim. to ISO 62
Density	1690	kg/m ³	ISO 1183

All information supplied by or on behalf of DSM in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and, in good faith, believed reliable, but DSM assumes no liability and makes no warranties of any kind, express or implied, including, but not limited to, those of title, merchantability, fitness for a particular purpose or non-infringement or any warranty arising from a course of dealing, usage, or trade practice whatsoever in respect of application, processing or use made of the aforementioned information or product. The user assumes all responsibility for the use of all information provided and shall verify quality and other properties or any consequence from the use of all such information. Typical values are indicative only and are not to be construed as being binding specifications.

Viscosity-shear rate



All information supplied by or on behalf of DSM in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and, in good faith, believed reliable, but DSM assumes no liability and makes no warranties of any kind, express or implied, including, but not limited to, those of title, merchantability, fitness for a particular purpose or non-infringement or any warranty arising from a course of dealing, usage, or trade practice whatsoever in respect of application, processing or use made of the aforementioned information or product. The user assumes all responsibility for the use of all information provided and shall verify quality and other properties or any consequence from the use of all such information. Typical values are indicative only and are not to be construed as being binding specifications.