

Granulati Termoplastici – Engineering Compounds

Identificazione: Sc 7.3.21 rev.01

PRODUCT**NEVIPOWDER PA6 27 1400 NATURALE**

Polyamide 6 powder

<i>Property</i>	<i>Value</i>	<i>Unit</i>	<i>Method</i>
Density	1,13	g/cm ³	ISO 1183
Viscosity number	152	cm ³ /g	ISO 307, 1157, 1628
Melting point (10°C/min)	220	°C	ISO 11357-1/-3
Water absorption	9.5	%	Similar to ISO 62
Moisture absorption	2.5	%	Similar to ISO 62
Granulometric distribution	µm	%	
	> 1400	0	
	> 1000	20	
	> 710	18	
	> 500	18	
	> 355	24	
	> 0	20	

REVISION DATE: 29/JUN/2012
REVISION INDEX: 00

Nevicolor makes no warranties and assumes no liability in connection with any use of this information