

Tecnoflon® VPL 85540 / VPL 55540 fluoroelastomer

Tecnoflon® VPL 85540 and 55540 belong to a brand new generation of very low temperature peroxide curable FKM. They have been designed to offer outstanding low temperature flexibility (i.e. TR10 = -40°C). Like all other Tecnoflon® peroxide curable grades, they exhibit excellent processability and superior mechanical properties and sealing ability; moreover they need very short post curing cycles.

Some of the basic properties of Tecnoflon® VPL 85540 and 55540 are:

- Outstanding low temperature behavior
- Very good chemical resistance
- Low post cure
- Superior mold flow
- Lack of mold fouling

- Excellent mold release
- Very good chemical resistance

Solvay offers medium (VPL 85540) and low viscosity (VPL 55540) versions in order to fulfil all customer's requirements. Accordingly to the curing technology, Tecnoflon® VPL 85540 and VPL 55540 can be transformed by all the molding techniques, including injection, injection-compression, compression and transfer molding. Tecnoflon® VPL 85540 and 55540 can be used with all typical peroxide curing system and the other fluoroelastomer compounding ingredients. Mixing can be accomplished with two-roll mills or internal mixers. This material can be extruded into hoses or profiles or can be calendered to make sheet stocks or belting.

[Click here for full datasheet.](#)

Tecnoflon® VPL 85540 / VPL 55540

fluoroelastomer

General

Material Status	• Commercial: Active	
Availability	• Europe	• North America
Features	• Chemical Resistant • Fast Cure • Good Flow • Good Heat Seal	• Good Mold Release • Good Processability • Low Temperature Flexibility • Medium-low Viscosity
Uses	• Belts/Belt Repair • Blending • Hose	• Low Temperature Applications • Profiles • Sheet
Appearance	• Translucent	
Forms	• Slab	
Processing Method	• Calendering • Compounding • Compression Molding	• Extrusion • Injection Molding • Resin Transfer Molding

Physical

	Typical Value	Unit
Mooney Viscosity		
ML 1+10, 121°C ¹	25	MU
ML 1+10, 121°C ²	45	MU
Fluorine Content ³	65	%

Notes

Typical properties: these are not to be construed as specifications.

¹ Raw polymer: VPL 55540

² Raw polymer: VPL 85540

³ Raw polymer

Tecnoflon® VPL 85540 / VPL 55540

fluoroelastomer

www.solvay.com

SpecialtyPolymers.EMEA@solvay.com | Europe, Middle East and Africa

SpecialtyPolymers.Americas@solvay.com | Americas

SpecialtyPolymers.Asia@solvay.com | Asia and Australia

Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products.

Neither Solvay Specialty Polymers nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Solvay's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Solvay's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right.

All trademarks and registered trademarks are property of the companies that comprise the Solvay Group or their respective owners.

© 2019 Solvay Specialty Polymers. All rights reserved.

