

Veradel® 3000RP

polyethersulfone

Veradel® 3000RP hydroxyl-functionalized polyethersulfones (r-PESU) is an amorphous, high-temperature sulfone polymer featuring reactive end groups to enhance solubility for dissolving or dispersing into solutions and to improve adhesion to substrates when used as a coating.

Veradel® 3000RP r-PESU offers excellent toughness and outstanding hydrolytic resistance. It resists attack from steam, boiling water and mineral acids. Cast films or coatings of r-PESU are transparent and have additional desirable properties, including long term thermal stability, excellent metal adhesion and formability and inherent flame resistance.

Veradel® r-PESU polymers are available in two molecular weight regimes. Veradel® 3000RP is a high molecular

weight sulfone polymer with a relatively low level of functionality while Veradel® 3600RP has a lower molecular weight sulfone polymer (approximately half the molecular weight of the Veradel® 3000RP) with roughly 3-5 times higher level of functionality. The differences in molecular weight results in highly varied levels of viscosity, when measured under similar conditions.

Typical applications include high-temperature coating formulations and specialty adhesives.

All Veradel® r-PESU polymers are produced at Solvay's state-of-the-art, world-scale facility in Panoli, India under ISO 9001:2000 and ISO 14001:2004 certified quality management systems.

General

Material Status	• Commercial: Active	
Availability	• Africa & Middle East • Asia Pacific • Europe	• Latin America • North America
Features	• Acid Resistant • Chemical Resistant • Creep Resistant • Flame Retardant • Food Contact Acceptable • Good Adhesion • Good Dimensional Stability • Good Thermal Stability	• Good Toughness • High Heat Resistance • High Molecular Weight • High Tensile Strength • Hydrolysis Resistant • Low Flow • Medium Rigidity
Uses	• Adhesives • Cast Film	• Coating Applications
Agency Ratings	• NSF STD-51	
RoHS Compliance	• Contact Manufacturer	
Appearance	• Transparent - Slight Yellow	
Forms	• Granules	• Powder
Processing Method	• Cast Film • Coating	• Solution Processing • Spraying

Physical

	Typical Value	Unit	Test method
Solution Viscosity			Internal Method
--1	700	mPa·s	
--2	5000	mPa·s	
Moisture Content - Measured at time of packing	1.5	%	Internal Method
OH End Groups - Titration	50	µeq/g	Internal Method
Particle Size - D50 Sieve measurement	250	µm	Internal Method

Veradel® 3000RP

polyethersulfone

Physical	Typical Value	Unit	Test method
Residual Solvent - Gas Chromatography	1.5	%	Internal Method

Mechanical	Typical Value	Unit	Test method
Tensile Modulus	2700	MPa	ASTM D638
Tensile Strength	90.0	MPa	ASTM D638
Tensile Elongation (Yield)	6.5	%	ASTM D638
Flexural Modulus	2600	MPa	ASTM D790
Flexural Strength	2.60	MPa	ASTM D790

Impact	Typical Value	Unit	Test method
Notched Izod Impact	53	J/m	ASTM D256

Thermal	Typical Value	Unit	Test method
Glass Transition Temperature	220	°C	DSC

Notes

Typical properties: these are not to be construed as specifications.

¹ 25% solution in DMAc at 40°C (measured at 25% solids)

² 35% solution in DMAc at 40°C (measured at 25% solids)

www.solvay.com

SpecialtyPolymers.EMEA@solvay.com | Europe, Middle East and Africa

SpecialtyPolymers.Americas@solvay.com | Americas

SpecialtyPolymers.Asia@solvay.com | Asia and Australia

Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products.

Neither Solvay Specialty Polymers nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Solvay's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Solvay's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right.

All trademarks and registered trademarks are property of the companies that comprise the Solvay Group or their respective owners.

© 2020 Solvay Specialty Polymers. All rights reserved.

