



Unipetrol RPA

You are here > [Unipetrol RPA](#) > [Our Products](#) > [Petrochemical Products](#) > [Polyolefins](#)

Font size: [A](#) [A](#) [A](#)

Refinery Products ▾

Petrochemical Products ▾

Monomers, Aromatics and
Other Petrochemical Products

Polyolefins

Agrochemicals ▾

Carbon Black CHEZACARB ▾

Power Engineering Products ▾

Business Conditions ▾

Safety Sheets and
Announcements ▾

Product Information

LITEN MB 61

Characteristic

LITEN MB 61 is a linear polyethylene, homopolymer with narrow molecular weight distribution, intended for injection moulding. It is suitable for manufacture crates, pallets, technical parts and other products requiring good rigidity and impact strength.

Typical properties and usage

Property	Unit	Typical value	Testing method
MELT FLOW RATE (190/2,16)	g/10 min	7.00	ISO 1133
MELT FLOW RATE (190/5)	g/10 min	20.00	ISO 1133
MELT FLOW RATE (190/21,6)	g/10 min	-	ISO 1133
DENSITY	kg/m ³	961	ISO 1183
YIELD STRESS	MPa	24	ISO 527
TENSILE STRAIN AT YIELD	%	9.0	ISO 527
FLEXURAL MODULUS	MPa	1050	ISO 178
CHARPY NOTCHED IMPACT STRENGTH 23°C	kJ/m ²	7.0	ISO 179
CHARPY NOTCHED IMPACT STRENGTH -30°C	kJ/m ²	-	ISO 179
VICAT SOFTENING TEMPERATURE	°C	126	ISO 306
SHORE HARDNESS D	-	58	ISO 868
ESCR F50; 50 °C; 100% DETERGENT	h	-	ASTM D1693
CONTENT OF CARBON BLACK	%	-	ISO 6469

Notice:

Data from table are represent typical values of each property. It is informative data, i.e. doesn't extent of specification of this type.

LITEN MB 61 meets the hygienic requirements on materials and articles intended for contact with foodstuffs according to Regulation (EC) 1935/2004 of the European Parliament and of the Council, as well as according to Commission Regulation (EU) No 10/2011 including changes and additions.

Print | Email | Back | Top

NEWSLETTER