



TECHNICAL DATA SHEET

Product	EP 50/5
Gruppo✓ Group	Plastificati Flexible
Categoria✓ Categorie	Estrusione Guarnizioni e Profili vari Gaskets and Profiles Extrusion
Emissione: 1 del 11/96 Revisione: 2 del 04/2009	

TECHNICAL INFORMATION	TESTING METHOD	UNIT OF MEASURE	VALUE
Peso Specifico Specific Weight	ISO 1183	g/cm ³	1,170
Durezza Hardness	ISO 868	Shore A	51
Carico di Rottura Tensile Strength	ISO 527	N/mm ²	10
Allungamento a Rottura Elongation at Break	ISO 527	%	420
Temp. di Irrig. a Torsione Cold Flex	ISO 458	°C	- 50
Stabilità Termica Heat Stability	ISO 182A	Minutes	50
Infiammabilità Inflammability	UL 94 (internal test) FIAT 7-G2000; ISO 3795*	Class	HB Slow Combustion
Applicazioni	Compound per estrusione articoli vari.		
Note	Le caratteristiche tecniche sopra riportate derivano da nostre analisi di laboratorio su campioni rappresentativi e sono da considerarsi valori medi tipici misurati sul prodotto e non possono essere usati come valori di specifica. Analisi eseguite su prodotto naturale non colorato * Spessore di 3 mm		
Applications	Compound for general purpose articles extrusion.		
Notes	The above mentioned technical characteristics come from our laboratory tests done on representative samples. They have to be considered as average typical values measured on the product and can not be used as technical specification values. Analyses referred to natural material without pigments. * Thickness of 3 mm		