

Tenac™ 3010

Asahi Kasei Corporation - Acetal (POM) Homopolymer

Tuesday, May 31, 2016

ASTM D785

94

120

	General Info	rmation		
General				
Material Status	Commercial: Active			
Availability	 Africa & Middle East Asia Pacific	EuropeNorth America		
Features	 Creep Resistant Fatigue Resistant Good Dimensional Stability	Good ToughnessHigh Impact ResistaHigh Stiffness	ince	 High Strength High Viscosity Homopolymer
Uses	Automotive ApplicationsBearingsConveyor Parts	Engineering PartsFastenersGears		• Housings
Automotive Specifications	 BMW 601.00.0 BOSCH 5515213 022 BOSCH 5515213 902 Color: Black BOSCH N28 BN21 Color: Black 		3 7-A1	ITT SWF 20.100 VDO MV 4831 VOLKSWAGEN KTHC 909
	ASTM & ISO P	•		
Physical		Nominal Value	Unit	Test Method
Specific Gravity		1.42	g/cm³	ASTM D792 ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 k	g)	2.8	g/10 min	ISO 1133
Molding Shrinkage - Flow		1.8 to 2.2	%	Internal Method
Water Absorption (23°C, 24 hr, 50% RH)		0.20	%	ASTM D570
lechanical		Nominal Value	Unit	Test Method
Tensile Modulus		3000	MPa	ISO 527-2
Tensile Stress				
Yield		70.0	MPa	ISO 527-2
		69.0	MPa	ASTM D638
Tensile Elongation (Break)		50	%	ASTM D638 ISO 527-2
Flexural Modulus				
		2700	MPa	ASTM D790
		2800	MPa	ISO 178
Flexural Strength		96.0	MPa	ASTM D790
Taber Abrasion Resistance		13.0	mg	ASTM D1044
mpact		Nominal Value	Unit	Test Method
Charpy Notched Impact Strength		13	kJ/m²	ISO 179
Notched Izod Impact		120	J/m	ASTM D256
Hardness		Nominal Value	Unit	Test Method

Disclaimer:

Rockwell Hardness

M-Scale

R-Scale

- Data shown are typical values obtained by proper testing methods and shoud not be used for specification purpose.
- Please use these data for selecting the most appropriate grade suitable for specific usage.
- These data may be changed because of improvement in properties.
- Be sure to read the relevant SDS before handling and use, and always follow the Important Precautions.
 Do not use plastics in any of the following orally-or medically-related applications.
- Orally-related application: any part, device or component which may come into direct oral contact or into direct contact with drinking foods or beverages. For drinking water application, please consult Asahi Ksei Chemicals Corporation.
- Medically-related applications : any part,or component which may be used intracorporeally or which may in dialysis or other processes come into direct or indirect contact with body tissue , body fluids , or transfusion fluids.

Tenac™ 3010

Asahi Kasei Corporation - Acetal (POM) Homopolymer

Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed	172	°C	ASTM D648
0.45 MPa, Unannealed	163	°C	ISO 75-2/B
1.8 MPa, Unannealed	133	°C	ASTM D648
1.8 MPa, Unannealed	100	°C	ISO 75-2/A
CLTE - Flow	1.0E-4	cm/cm/°C	ASTM D696 ISO 11359-2
Specific Heat	1470	J/kg/°C	
Thermal Conductivity	0.23	W/m/K	
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+16 to 1.0E+17	ohms	ASTM D257
Volume Resistivity (23°C)	1.0E+15 to 1.0E+16	ohms·cm	ASTM D257
Dielectric Strength	18	kV/mm	ASTM D149
Dielectric Constant (23°C, 1 MHz)	3.80		ASTM D150
Dissipation Factor (23°C, 1 MHz)	7.0E-3		ASTM D150
Arc Resistance	250	sec	ASTM D495
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.50 mm)	НВ		UL 94

Notes

Disclaimer:

- Data shown are typical values obtained by proper testing methods and shoud not be used for specification purpose. Please use these data for selecting the most appropriate grade suitable for specific usage.
- These data may be changed because of improvement in properties.

 Be sure to read the relevant SDS before handling and use, and always follow the Important Precautions.

 Do not use plastics in any of the following orally-or medically-related applications.
- Orally-related application: any part, device or component which may come into direct oral contact or into direct contact with drinking foods or beverages.
- For drinking water application, please consult Asahi Ksei Chemicals Corporation.

 Medically-related applications: any part, or component which may be used intracorporeally or which may in dialysis or other processes come into direct or indirect contact with body tissue, body fluids, or transfusion fluids.

¹ Typical properties: these are not to be construed as specifications.