

SABIC® PP 579S

POLYPROPYLENE HOMOPOLYMER FOR INJECTION MOLDING

DESCRIPTION

SABIC® PP 579S is a PP grade with narrow molecular weight distribution. This grade is formulated with antistatic and nucleating agents. It is suitable for producing thin-walled injection molding articles and it gives low warpage tendency, high stiffness & outstanding flow properties for excellent part filling.

TYPICAL APPLICATIONS

SABIC® PP 579S can be used mainly for thin-walled applications, houseware, appliances, caps & closures.

TYPICAL PROPERTY VALUES

Revision 20170531

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES			
Melt Flow Rate			
@ 230°C & 2.16kg load	47	g/10 min	ASTM D 1238
Density at 23°C	905	kg/m ³	ASTM D792
MECHANICAL PROPERTIES			
Tensile Strength at Yield	35	MPa	ASTM D638
Tensile Elongation at Yield	11	%	ASTM D638
Flexural Modulus (1% Secant)	1900	MPa	ASTM D790
Notched Izod Impact Strength at 23°C	20	J/m	ASTM D256
Rockwell Hardness, R-Scale	104	-	ASTM D785
THERMAL PROPERTIES			
Vicat Softening Point	152	°C	ASTM D1525
Heat Deflection Temperature at 455kPa	98	°C	ASTM D648

PROCESSING CONDITIONS

Barrel temperature range: 200 - 250°C Mold Shrinkage: 1.2 - 2.5% depending on wall thickness and Processing conditions. Mold Temperature: Normally 15 - 40°C, up to 65°C for thick parts.

HEALTH, SAFETY AND FOOD CONTACT REGULATIONS

SABIC® PP 579S is suitable for food contact application. Detailed information is provided in relevant documents / certificates and for additional specific information please contact SABIC local representative.

DISCLAIMER: This product is not intended for and must not be used in any pharmaceutical / medical applications.



STORAGE AND HANDLING

Polypropylene resin should be stored in a manner to prevent a direct exposure to sunlight and/or heat. The storage area should also be dry and preferably do not exceed 50°C. SABIC would not give warranty to bad storage conditions which may lead to quality deterioration such as color change, bad smell and inadequate product performance. It is advisable to process PP resin within 6 months after delivery.

DISCLAIMER

The information contained herein may include typical properties of our products or their typical performances when used in certain typical applications. Actual properties of our products, in particular when used in conjunction with any third party material(s) or for any non-typical applications, may differ from typical properties.

It is the customer's responsibility to inspect and test our product(s) in order to satisfy itself as to the suitability of the product(s) for its and its customers' particular purposes. The customer is responsible for the appropriate, safe and legal use, processing and handling of all product(s) purchased from us.

Nothing herein is intended to be nor shall it constitute a warranty whatsoever, in particular, warranty of merchantability or fitness for a particular purpose.

SABIC as referred to herein means any legal entity belonging to the group of companies headed by Saudi Arabia Basic Industries Corporation.