



TECHNICAL DATA SHEET

Product	SN 58/E-N
Gruppo✓ Group	Plastificati Flexible
Categoria✓ Categorie	Stampaggio Calzature Footwear Injection Moulding
Emissione: 1 del 05/2013 Revisione: 0 del 05/2013	

TECHNICAL INFORMATION	TESTING METHOD	UNIT OF MEASURE	VALUE
Peso Specifico Specific Weight	ISO 1183	g/cm ³	1,180
Durezza Hardness	ISO 868	Shore A	57 (PI)
Carico di Rottura Tensile Strength	ISO 527	N/mm ²	8,5
Allungamento a Rottura Elongation at Break	ISO 527	%	390
Temp. di Irrig. a Torsione Cold Flex	ISO 458	°C	
Stabilità Termica Heat Stability	CEI 20-34/3-2	Minutes	45
Applicazioni	Stampaggio articoli tecnici e calzature. Esente da piombo. Conforme a direttiva 2011/65/EU (RoHS), 2003/11/CE. PI = Pressa iniezione		
Note	Le caratteristiche tecniche sopra riportate derivano da nostre analisi di laboratorio su campioni rappresentativi e sono da considerarsi valori medi tipici misurati sul prodotto e non possono essere usati come valori di specifica. Analisi eseguite su prodotto naturale non colorato.		
Applications	Technical articles and footwear injection moulding. Lead free. In according to directive 2011/65/EU (RoHS), 2003/11/CE. PI = Injection moulding press		
Notes	The above mentioned technical characteristics come from our laboratory tests done on representative samples. They have to be considered as average typical values measured on the product and can not be used as technical specification values. Analyses referred to natural material without pigments.		